



1K Satin Wood Polyurethane Decking

"Selchem the designers choice"

PRODUCT BENEFITS

- High performance exterior clear varnish.
- Contains ultra violet light absorbers to protect the coating and the wood.
- Gives up to 50% more life than conventional varnishes.
- Excellent film clarity and appearance imparts gloss in depth.

USES

For use on all external timber where only the best quality varnish is required. Combines a tough, glossy finish with "double life" durability.

GENERAL DATA

Type Alkyd modified with UV absorbers

Drying Time Touch Dry 4 hours

Recoating Time 18 hours (overnight)

Solids by Volume 44 - 46%

Gloss Level High Gloss

Spreading Rate Approx. 10 m² per litre depending on surface porosity profile.

COLOUR RANGE

- Clear

APPLICATION

Brush

Ready for use. Rollers are not recommended.

Conventional Spray

Thin up to 25% with Mineral Turpentine. Thinning reduces film build and gloss.



"Selchem the designers choice"



1K Satin Wood Polyurethane Decking

"Selchem the designers choice"

Spraying does not improve life.

- Thinner : Mineral Turpentine
- Cleanup : Mineral Turpentine or FIXIT BRUSH CLEANER/DEGREASER

SURFACE PREPARATION

NEW SURFACES

New exterior surfaces must be clean, dry and well sanded. Thin first coat with 10% Mineral Turpentine. Second and third coats should be applied unthinned. Slightly between coats.

PREVIOUSLY VARNISHED SURFACES

Sound surfaces should be well sanded. Surfaces which are cracked and flaked must be stripped to bare wood either by sanding or by the use of FIXIT DOUBLE STRENGTH PAINT REMOVER. Sand any discolored wood to fresh wood. For maximum protection of exterior timber, apply three coats of varnish.

PRECAUTIONS

- For detailed safety information refer to the Material Safety Data Sheet [MSDS](#)
- It is important to varnish the end grain of exterior timber to prevent ingress of moisture.
- Do not apply to wet or damp timber.

FLASH POINT

37 °C

"Selchem the designers choice"